



## Technical Data Sheet

### IMPULSE 80GR

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m <sup>2</sup>	80 +/- 3%
Thickness	ISO 534	µm	105 +/- 4
Bulk	ISO 534		1,31
Moisture Content	ISO 287	%	4,2 +/- 0,5
Roughness	ISO 8791	Bendtsen ml/min	200 +/- 50
Whiteness	ISO 11475	CIE	161 +/- 3
Opacity	ISO 2471	%	91 +/- 2
Stiffness MD	ISO 2493	m/N	110 +/- 10
Stiffness CD	ISO 2493	m/N	45 +/- 5

#### Production sites:

The production mills operate in compliance with the following standards



#### Special Attributes:



References:  
Product is made taking into account requirements of DIN EN 12281  
Product made from ECF Pulp  
ISO 18001 - OHSAS Health & Safety

The data presented can be changed without notice.

International Paper EMEA  
Chaussée de la Hulpe 166  
1170 Brussels, Belgium  
Tel.: +32 2 774 1211  
Fax: +32 2 774 1299  
Extract date: 19.01.2017